

Technical Data Sheet

POLYURETHANE 2:1 COLOR



PRODUCT DESCRIPTION

Two pack polyurethane topcoat in high gloss.

Is characterized by high coating strength, UV resistance, maritime atmosphere and scratches. Sea-Line Polyurethane topcoat after hardened can be polish. Particularly recommended to protect surface above water line, optionally can be used below water line but it doesn't protect against fouling. Product for professional use only.

PRODUCT INFORMATION

SURFACE TYPE	laminate, wood, aluminum , steel
COLOR	white, ecru, red, navy blue, blue, green, grey, black
GLOSS	high gloss
VOLUME SOLIDS	53-58% (depending on color)
DENSITY	1,0-1,1kg/l(depending on color)
VOC	depending on color, information available on info@sea-line.eu
MIXING RATIO	2:1 by volume (ml)
THEORETICAL COVERAGE	13÷14 m ² /l for thickness 75µm (WFT) / 40µm (DFT)
METHODE OF APPLICATION	Brush, roll, pneumatic spray gun

INSTRUCTION FOR USE

SURFACE PREPARATION **NEW BOAT without previous paint coats** salt and other contaminations remove with pressurized fresh water after that wait until surface is dry. Next step is to sand surface by abrasive paper P320-P600. Remove dust and degrease surface using Sea-Line Cleaner.

OTHER all paints and primers 1K and 2K paints in poor condition or damage should be removed. If 2K paint is in good condition, sand surface to uniform roughness. Remove dust and degrease surface using Sea-Line Cleaner.

It is recommended to prime the surface before applying the topcoat. Using primer we get better adhesion between paint systems and protect surface. Check TDS for specific primer.

PRODUCT PREPARATION This product is two pack product. Always mix components in accordance to mixing ratio. Component A is the base, Component B is the hardener. Once mixed, set should be used before pot life expiration- see chapter pot life. For diluting products, add thinner recommended by producer in proper mixing ratio. Thinning level depends on method of application, tools, air temperature, paint viscosity. Percentage dilution ratio see in chapter thinning. Mix all components thoroughly and wait for air bubbles to disappear.

MIXING RATIO 2:1 by volume (ml)

THINNING For thinning it is recommend to use Sea-Line Thinner for polyurethane. Depends on method of application choose:

Thinner for brush or roll application

Thinner for spray application

Color	Brush/roll	Pneumatic spray
white	20-25%	50-55%
ecru		
red	15-20%	45-50%
navy blue		
blue		
green		

Technical Data Sheet

POLYURETHANE 2:1 COLOR



grey	15-20%	45-50%
black		

APPLICATION

Number of coats 1-3 layers

Pot life 3h (20°C)

Spray parameters

Pneumatic spray

gravity fed	1,3 - 1,4 mm
pressure	2-3 bar

CURING INFORMATION

Temperature	Overcoating interval	Dust dry	Dry to polish	Fully hardened
20°C	minimum 30 min	6-8 h	24 h	7 days
10°C	minimum 60 min	12-16 h	48 h	14 days

The given times must be considered as a guideline only. The actual drying time may be longer or shorter depending on film thickness, ventilation, humidity etc.

IMPORTANT NOTES

Product temperature should be minimum 15°C and max. 35°C. Ambient and surface temperature should be more than 5°C and lower than 30°C.
High relative humidity or condensation within the first 24 hours after application may adversely affect the formation of coating.

Do not apply two pack paint over one pack products. Avoid painting in direct sunlight. For degreasing, use Sea-Line Cleaner.

It is not recommended to paint surfaces which were previously protected with oils or products containing oils.

It is not recommended for oily wood types like teak, ipe, etc.

Immersion should be done only after when the last layer of primer and topcoat paint have hardened. When polyurethane is painted below water line, boat shouldn't be on the water all the time, after sailing boat should be pulled out from the water.

FURTHER WORK

When occur paint film defects, it can be removed by sanding surface P1200-P1500 as a finish gradation and after that use polishing compound

S1 PREMIUM ONE STEP CUT & HIGH GLOSS

S1 SOFT CUT & GLOSS

Finish stage:

S2 EXTRA SHINE HOLOGRAM REMOVER

Protect surface:

S5 QUICK WAX

STORAGE AND SAFETY INFORMATION

SHELF LIFE

Base (component A) 12 months from production date

Hardener (component B) 9 months from production date

STORAGE

Product components should be stored in tightly sealed containers, in a temperature of 10-25°C, away from sources of fire, heat and sunlight. Close container tightly

Technical Data Sheet

POLYURETHANE 2:1 COLOR



immediately after each use. Store in a dry place and keep sealed cans until use. The hardener is moisture sensitive! Store tins in a dry place and keep them tightly closed until the moment of use. Even the smallest trails of water in mixed paint will cause shortening of use-by date and, as a result, flaws in surface.

HSE CONDITIONS

Please follow safety instructions from the Safety Data Sheet for hazardous chemical and follow workplace safety laws. The general rule is to avoid contact of the product with the skin and eyes. When product is used in a small, closed spaces you must provide forced ventilation. It is also recommended that you protect your respiratory system, eyes, and skin. Special care should be taken in the area of fire protection and explosion hazards. **Notice ! Always follow all precautionary, health and safety notice on the Safety Data Sheet and container labels.**

DISCLAIMER

All data in this document have been prepared for informational purpose only. We can not take responsibility for the results of user actions over which we have no control. The user is responsible for making the control sample and determining the suitability of the product for specific, individual applications. Company Troton Sp. z o.o. does not take responsibility for any damage, or loss of profits associated with the improper use of the products. All information is based on scrupulous laboratory research and many years of experience. Our position of market leadership does not free us from constant quality control of our products. However, we do not accept responsibility for the effects of improper use or storage of our products, or the effects of using our products in any way contrary to the standard of good workmanship.

QUALITY GUARANTEE

Production, quality control and the realization of deliveries fulfill the demands of ISO 9001 and 14001 standards.